



**ProWise  
9127  
High Build Latex Flat**

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Latex	Flat	350 - 400 Sq Ft Per Gallon	Brush, Roller, Pad or Airless Spray	Clean Water	Warm Soapy Water	30 Minutes	4 Hours	30 Days
<b>PRODUCT NAME:</b> 9127 ProWise High Build Latex Flat		This latex flat coating is designed to provide good dry hide and an excellent matte flat appearance when applied to properly prepared surfaces. Exhibits good touch-up properties. Formulated exclusively for production work such as apartment and commercial construction.						
<b>WHERE TO USE:</b>		Drywall Plaster Wood Cement Block Metal  An ideal flat coating to be used for in rental property maintenance, apartments or for budget minded consumers. <b>NOTE:</b> Not for use in areas that are frequently washed or scrubbed.						
<b>Surface Preparation:</b>		<b>New Work:</b> The surface to be coated must be clean and free of dust, grease, wax, rust, oil, and bleeding stains.  <b>Priming –</b> Drywall – Prime with ProWise PVA Primer 125-00 or this product. Plaster – Prime with 145 CeramicWise Primer Wood – Prime with ProWise PVA Primer 125-00 or this product. Ferrous Metal – Rust inhibiting metal primer such as #35-11, #2090 or #925-147. Non-Ferrous Metal – Dull new non-ferrous metal with a maroon scrub pad and Prime with 145 CeramicWise Primer. Masonry – Prime with poured or precast masonry with 145 CeramicWise Primer. Fill porous block with 126 ProWise Latex Block Filler.  <b>Repaint Work:</b> Remove any oil, chalk, dirt, wax or dust prior to re-coating. Any loose or flaking paint should be removed, patched and the edges feather sanded to produce a smooth, uniform surface. Dull glossy surfaces to insure good adhesion. On previously painted surfaces in good repair, no priming is generally necessary. Spot prime bare areas with this product or the primer indicated above.						
<b>Application:</b>		Stir product thoroughly with a circular, lifting motion to disperse into a homogenous liquid. Roller – 3/8” to 1-1/4” nap, depending on surface texture. Brush – Nylon or polyester filament Airless Spray – Tip size and atomization pressures will vary with type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern. Best results are more likely obtained by using quality application tools. Do not apply directly over chalky surfaces or bleeding stains.						
<b>NOTE: Formulated without mercury or lead.</b>								

<b>Resin Type:</b>	Vinyl Acetate Acrylic Copolymer
<b>Solids:</b>	Weight – 43.0% Volume – 26.9%
<b>Weight Per Gallon:</b>	10.60 lbs.
<b>Viscosity:</b>	98 - 100 (Krebs Units)
<b>Specular Gloss:</b>	2 - 6% @ 85 Degrees
<b>Recommended Film Thickness:</b>	Wet – 3.5 to 4.5 mils Dry – 1.0 to 1.22 mils
<b>VOC – VOS Statement:</b>	This product contains less than 0.42 lbs per gallon of coating or 50 GPL.
<b>Cautions:</b>	<b>CAUTION!</b>  <b>Do not take internally. Close container after each use.</b>  <b>KEEP OUT OF REACH OF CHILDREN.</b>